


NATURAL BioZinalium pipes with notches (CONTROL+) DN150 to 1000 with STANDARD socket (preferred pressure classes)



DN	Lu (m)	Class	e (mm)	ØDE (mm)	ØDI (mm)	P (mm)	ØB (mm)	Mass (kg/m)	References
150	6.00	C40	4.5	170	173.4	100.5	220.8	22.15	NSB15Q60AQV
200	6.00	C40	4.7	222	225.2	106.5	275.1	30.20	NSB20Q60AQV
250	6.00	C40	5.5	274	276.8	105.5	328.6	42.22	NSB25Q60AQV
300	6.00	C40	6.2	326	328.8	107.5	385.3	55.55	NSB30F60AQV
350	6.00	C30	6.4	378	380.9	110.5	444.5	68.83	NSB35G60AQV
400	6.00	C30	6.5	429	431.9	112.5	494.6	79.40	NSB40G60AQV
450	6.00	C30	6.9	480	483	115.5	546.5	93.80	NSB45G60AQV
500	6.00	C30	7.5	532	535	117.5	600.9	111.15	NSB50G60AQV
600	6.00	C30	8.7	635	638.1	132.5	712	150.57	NSB60G60AQV
800	6.95	C25	9.6	842	845.8	197	935.6	229.00	NSB80H70AQV

* DN700-900-1000: Please contact us

Case CONTROL+

Description	Mass (kg)	References
Case CONTROL+	6.50	278397

Legend:

- DN: nominal diameter
- Lu: laying length, in m
- Class: pressure class according to EN 545 and ISO 2531
- e: nominal thickness according to ISO 2531, in mm
- ØDE: external nominal diameter of the barrel according to EN 545 and ISO 2531, in mm
- ØDI: internal nominal diameter of the socket, in mm
- P: nominal depth of the socket, in mm
- ØB: nominal diameter of the socket, in mm
- Mass: total mass per metre (including cement coating and socket), determined with the nominal thickness, in kg/m
- Reference: commercial reference Saint-Gobain PAM

Field of use:

- For drinking water and other water network applications (except sewage water)

Main characteristics:

- Pressure class in conformity with Standard EN 545-2010 and ISO 2531-2009
- External **BioZinalium[®]** coating consists of two layers:
 - a layer of zinc-aluminium 85/15 alloy, enriched with copper, with a minimum surface density of 400g/m², applied by spraying molten metal onto the surface of the iron, using an electric arc spray gun, from ZnAl (Cu) alloy wire
 - a protective layer of Aquacoat (semi-permeable), a water-based blue acrylic of average thickness 80 microns applied using a spray gun (RAL 5005)
- Internal coating: sulfate resisting blast furnace cement mortar
- Standard joint SUREJOINT in alimentary elastomer EPDM (ACS, KTW, WRAS,...)
- Vi anchoring without bolts

Type of soils:

BioZinalium[®] coating can be in contact with all type of soil, as defined in Annex D.2.2 of EN545:2010, except:

- peaty and acid soils
- soils containing wastes, scraps, ashes, slags or soils contaminated by industrial effluents or other wastes
- soils located under the level of the marine water table with a resistivity lower than 500 Ω cm

In such soils, and also in the event of stray currents, it is recommended to use other types of external coatings for more aggressive soils (TT PE or TT PUX ranges).


Type of water:

NATURAL[®] ductile iron pipes with internal coating of sulphate resisting blast furnace cement mortar are adapted to convey all types of drinking water in conformity with Directive EU 2020/2184. In case of other type of water, please refer to below information:

	Minimum value	Maximum value			
Parameter	pH	CO2 aggressive	Sulphate	Magnesium	Ammonium
Unit	-	mg/l	mg/l	mg/l	mg/l
Value	5,5	15	3000	500	30

Blast furnace cement mortar is a sulphate resisting cement (SRC).

Fitting a SUREJOINT gasket



When installing the SUREJOINT STANDARD Gasket:

- Bend manually the joint to form a hart, having the connecting nozzle opposite of your hands.
- Begin the gasket positioning in the socket groove by introducing the nozzle in a notch of the pipe front face.
- Choose one notch on the upper section of pipe, in order that the nozzle remains accessible when in the trench.
- Continue the joint installation as usual with Standard one.

[User guide - Standard Gasket CONTROL+ Testing Device](#)


SUREJOINT quality check

The use of SUREJOINT Standard gasket, with the SUREJOINT Natural pipe, gives an immediate opportunity to check the integrity of the joint during installation. The check can detect any major defects during the jointing of the pipe, allowing any remedial work to be carried out straight away.


Checking of the joint is made by using the SUREJOINT testing device.

For full instructions of how to use SUREJOINT please refer to the Installation manual.


Linked products




Kit Standard Pipe with notches + Standard SUREJOINT (CONTROL+) Gasket




Gasket STANDARD rubber water EPDM SUREJOINT (CONTROL+) equipped with valve




Kit Standard Pipe with notches + Standard Gasket



Standard gasket for Pipes and Fittings DN60-2000



Kit Standard Pipe with notches + Standard Vi Gasket



STD Vi gasket for Pipes and Fittings DN60-700



Lubricating paste - BLUPAM



Lubricating paste - NATURAL, INTEGRAL, and PLUVIAL ranges

The information on this sketch is, to the best of our knowledge correct at the time of printing. However Saint-Gobain are constantly looking at ways of improving their products and services therefore reserve the right to change without prior notice, any of the data shown. Any orders placed will be subject to our Standard Conditions of Sale, available on request.