


## ZMU pipes DN100 to 300 with UNIVERSAL TYTON socket + Weld bead Ve



DN	Lu (m)	Class	e (mm)	e1 (mm)	ØDE (mm)	ØDI (mm)	P (mm)	ØB (mm)	Bead position c (mm)	Mass (kg/m)	References
100	5.97	C100	6.1	5	118	120.5	140	188	90	23.30	177976
125	5.97	C64	6.1	5	144	146.5	139.9	203	95	28.60	207489
150	5.97	C64	6.2	5	170	172.5	148	230	95	34.40	173680
200	5.97	C64	6.5	5	222	224.5	155	290	100	47.00	172994
250	5.97	C50	6.8	5	274	276.5	166	350	110	60.90	177980
300	5.97	C50	7.4	5	326	328.5	180	408	115	77.60	173701

### Legend:

- DN: nominal diameter
- Lu: laying length, in m
- Class: pressure class according to EN 545 and ISO 2531
- e: nominal thickness according to ISO 2531, in mm
- e1: external thickness of ZMU coating, in mm (cement mortar with acrylic fibers and resin) according to EN15542
- ØDE: external nominal diameter of the barrel according to EN 545 and ISO 2531, in mm
- ØDI: internal nominal diameter of the socket, in mm
- P: nominal depth of the socket, in mm
- ØB: nominal diameter of the socket, in mm
- c: weld bead position, in mm
- Mass: total mass per metre (including cement coating and socket), determined with the nominal thickness, in kg/m
- Reference: commercial reference Saint-Gobain PAM


## Field of use:

- For drinking water supply networks

## Main characteristics:

- Joint in alimentary elastomer EPDM (ACS, KTW, WRAS,...)
- External coating: a layer of zinc-aluminium 85/15 alloy, enriched with copper, with a minimum surface density of 400g/m<sup>2</sup>, applied by spraying molten metal onto the surface of the iron, using an electric arc spray gun, from ZnAl (Cu) alloy wire + a protective layer of Aquacoat (semi-permeable), a water-based blue acrylic of average thickness 80 microns applied using a spray gun + cement mortar ZMU with polymeric additiv and reinforced with PE fibers
- Internal coating: sulfate resisting blast furnace cement mortar
- ZMU pipes are in conformity with EN 545
- ZMU coating in conformity with EN 15542

## Type of soils:



ZMU coating can be in contact with nearly all types of soil. Please consider the following matrix based upon resistivity of soils. In case of doubt, please advise.

## Type of water:

Ductile iron pipes with internal coating of sulphate resisting blast furnace cement mortar (SRC) are adapted to convey all types of drinking water in conformity with Directive EU 2020/2184.


In case of other type of water, please refer to below information to check the compatibility with cement mortar.

	Minimum value	Maximum value			
Parameter	pH	CO2 aggressive	Sulphate	Magnesium	Ammonium
Unit	-	mg/l	mg/l	mg/l	mg/l


	Minimum value	Maximum value			
Value	5,5	15	3000	500	30

Other cement lining also available on request.


## Linked products



Kit Universal Tyton Ve  
ZMU Pipe + Universal  
Tyton Ve Joint



TYT Gasket for TYT Pipes  
and Fittings DN80-300



Locking Ring for UNI Ve  
joint DN80-1800



Lubricating paste -  
BLUPAM



Lubricating paste -  
NATURAL, INTEGRAL,  
and PLUVIAL ranges

*The information on this sketch is, to the best of our knowledge correct at the time of printing. However Saint-Gobain are constantly looking at ways of improving their products and services therefore reserve the right to change without prior notice, any of the data shown. Any orders placed will be subject to our Standard Conditions of Sale, available on request.*