

## EVA ring



Version	References
AMBER	CDAM60CW-J
DYNATOP	CDDY60AG-J
KORUM 600 / BELSYS 600	CDKO60BF-J
REXEL 2	CDRD60AF-J
REXESS	CDRK60FY-J
OPTEA 785 / R-TEX	CDRT60AWX-J
PAM GENIUS / PAM ESSENTIA	CDGE60AF-J

The color of the ring depends on the type of product chosen.

The composite ring of base of manhole covers ensures a great strength to the constraints of traffic, with crushing, with abrasion and et tiredness on a broad temperature range.

It is composed of ethylene vinyl acetate.

The comparative results carried out in laboratory show the following results:

Criterion	Improvement compared to the polyethylene ring	
Breaking strength	19,6 Mpa against 11,5 Mpa	+ 70 %
Behaviour with abrasion	Weight loss : 3,45 % against 10 %	Multiplied by 3
Temperature: Performance range	Of - 20 °C with + 70 °C	
Behaviour with tiredness	5000 cycles against 1900	Multiplied by 2, 6

The both principles criterions which influence over the shelf life of the ring in use (tire and rupture) were considerably improved and the broad beach of use in temperature satisfied to all climatic conditions. It's necessary to be ensured, during the handling of covers and notably before the closing, that the composite ring is free from dirtinesses and to clean if it's necessary.

The presence of dirtinesses (for example small stones) between the cover and the ring involves the premature degradation of this one.

In the event of degradation, it's imperative to change the ring quickly.

The change is carried out by unsnapping of degraded ring and reinstallation of a new ring adapted to the manhole cover.

*The information on this sketch is, to the best of our knowledge correct at the time of printing. However Saint-Gobain are constantly looking at ways of improving their products and services therefore reserve the right to change without prior notice, any of the data shown. Any orders placed will be subject to our Standard Conditions of Sale, available on request.*

*COPYRIGHT AND DESIGN RIGHT : This drawing is the exclusive property of Saint-Gobain PAM UK and is confidential and must not be reproduced or disclosed for any third party without written consent. It must be used only for the purpose for which it has been issued and is returnable on request*